

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C22C 21/02</b>		A1	(11) International Publication Number: <b>WO 95/06759</b>
			(43) International Publication Date: 9 March 1995 (09.03.95)
(21) International Application Number: PCT/GB94/01880 (22) International Filing Date: 30 August 1994 (30.08.94) (30) Priority Data: 9318041.2 31 August 1993 (31.08.93) GB (71) Applicant (for all designated States except US): ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street West, Montreal, Quebec H3A 3G2 (CA). (72) Inventors; and (73) Inventors/Applicants (for US only): YIU, Hang, Lam [GB/GB]; 13 Osterley Grove, Banbury, Oxon OX16 9LR (GB). RICKS, Ricky, Arthur [GB/GB]; "Tredgets", Wroslyn Road, Freeland, Oxon OX8 8AQ (GB). COURT, Stephen, Anthony [GB/GB]; 23 Twyford Gardens, Twyford, Nr. Banbury, Oxon OX17 3JJ (GB). (74) Agent: PENNANT, Pyers; Stevens, Hewlett & Perkins, 1 Serjeants' Inn, Fleet Street, London EC4Y 1LL (GB).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD). Published With international search report.	

(54) Title: EXTRUDABLE Al-Mg-Si ALLOYS

(57) Abstract

High strength high extrudability Al-Mg-Si alloys have the composition in weight %: Mg 0.25 - 0.40; Si 0.60 - 0.90; Fe up to 0.35; Mn up to 0.35 preferably 0.10 - 0.25.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

EXTRUDABLE Al-Mg-Si ALLOYS

5

This invention concerns intermediate strength extrudable Al-Mg-Si alloys, in the 6000 series of the Aluminum Association Register. The dilute Al-Mg-Si alloys, with levels of the two primary alloying additions at less than approximately 0.50 wt.%, are used extensively in extruded form in many market sectors, including architectural (doors, window frames, etc.) and structural applications. These alloys generally lie within the AA6063 specification, which has compositional limits for Mg and Si of 0.45 to 0.90 wt.% and 0.20 to 0.60 wt.% respectively. These alloys are capable of producing complex sections which are readily air quenchable off the press and which may be extruded at high exit speeds whilst maintaining a very high quality surface finish; attributes which are associated with high extrudability.

In one aspect, this invention is concerned with alloys of composition in weight %

	Mg	0.25 - 0.40
25	Si	0.60 - 0.90
	Fe	up to 0.35
	Mn	up to 0.35
	Others	up to 0.05 each, 0.15 total
	Balance Al.	

30

Reference is directed to Figure 1 of the accompanying drawings, which is a compositional plot showing the Mg and Si specification ranges for various alloys in the Aluminum Association specification. The filled circle shows the nominal composition of alloys according to the present invention, and the rectangle round it corresponds to the above definition. It can be

35

- 2 -

seen that the above defined alloy composition does not overlap with any of the AA designated alloys shown.

The alloys of the present invention are high excess Si alloys. The nominal composition of these alloys (marked by the filled circle in Figure 1) is set out in the table below, together with the nominal compositions of AA6106 which is an excess Si alloy, and of AA6063A which is a balanced alloy. An alloy of balanced composition is one in which just enough Si is present to combine with all the Mg, Fe, Mn as  $Mg_2Si$  and  $Al(Fe,Mn)Si$ .

Nominal Composition				
Alloy	Si	Mg	Fe	
Invention	0.70	0.35	0.2	
AA6106	0.6	0.5	0.2	
AA6063A	0.5	0.63	0.2	

The alloys of this invention have a number of advantages. It should be understood that not all the stated advantages are necessarily achieved by all the alloys. Also, a particular property may not be an improvement on some other alloy. But most of the advantages are possessed by most alloys according to the invention, and it is this combination that represents a significant advance in the art:

- Extrusion ingots of the alloys are capable of being extruded at relatively high speeds, typically around 75% of the maximum extrusion speed of AA6063 alloys.

- 3 -

- The extrusion pressures required are lower than for AA6063 alloys, which reduces equipment and operating costs.

- The extrusions are air quenchable.

5       - The extrusions have a surface quality which is acceptable for most architectural applications.

10       - By particular means, e.g. the addition of Mn as discussed below, the surface quality of the extrusions can be made to be better than for any related alloy compositions.

- The extrusions are capable of being aged to a tensile strength in excess of 240 MPa, often in excess of 250 MPa, with acceptable toughness.

15       - A two-stage or ramped ageing process is particularly effective in improving aged properties.

20       The Mg content of the invention alloy is set at 0.25 - 0.40%. If the Mg content is too low, it is difficult to achieve the required strength in the aged extrusions. Extrusion pressure increases with Mg content, and becomes unacceptable at high Mg contents.

25       The Si content is set at 0.6 - 0.9%. If the Si content is too low, the alloy strength is adversely affected, while if the Si content is too high, extrudability may be reduced. The function of the Si is to strengthen the alloy without adversely affecting extrudability, high temperature flow stress, or anodising and corrosion characteristics.

30       Fe is not a desired component of the alloy, but its presence is normally unavoidable. An upper concentration limit is set at 0.35%, and a preferred range at 0.15 - 0.35% (because alloys containing less Fe are more expensive). In the as-cast alloy ingot, Fe is present in the form of large plate-like  $\beta$ -AlFeSi particles. Preferably the extrusion ingot is  
35       homogenised to convert  $\beta$ -AlFeSi to the  $\alpha$ -AlFeSi form.

- 4 -

It is known however that excess Si (over the amount required to form  $Mg_2Si$ ) stabilises the  $\beta$ -AlFeSi phase, which has a detrimental effect on extrudability and in particular on extrusion surface quality. Where  
5 extrusion surface quality is important, this problem may be avoided by homogenising the extrusion ingot under special conditions or by modifying the alloy composition.

Preferably Mn is included in the alloys in  
10 order to improve extrusion surface quality. Mn acts to accelerate the  $\beta$  to  $\alpha$ -AlFeSi transformation during homogenisation, so that the resulting homogenised ingot has improved extrudability, that is to say improved extrusion surface quality. Any Mn addition is  
15 beneficial in this way and improvements may be seen with additions as low as 0.05% or 0.07%. Above 0.35% Mn, further improvements are not seen, or are not commensurate with the added cost, and the extrudates may show increased quench sensitivity. A preferred Mn  
20 content is 0.10 - 0.25%.

In the age-hardened extrusions, it is apparent that some of the Si is present as  $Mg_2Si$  and some more is present as AlFeSi. In preferred compositions according to the invention, the excess Si,  
25 over the amount required to combine with all the Mg and Fe present, is at least 0.3%.

An extrusion ingot of the alloy of the invention may be made by any convenient casting technique, e.g. by a DC casting process preferably by  
30 means of a short mould or hot-top DC process. The Fe is preferably present as an insoluble secondary phase in the form of fine  $\beta$ -AlFeSi platelets preferably not more than 15  $\mu m$  in length or, if in the  $\alpha$  form, free from script and coarse eutectic particles.

35 The as-cast extrusion ingot is homogenised, partly to bring the soluble secondary magnesium-silicon

- 5 -

phases into suitable form, and partly to convert  $\beta$ -AlFeSi particles into  $\alpha$ -AlFeSi particles, preferably below 15  $\mu\text{m}$  long and with 90% below 6  $\mu\text{m}$  long.

Homogenisation typically involves heating the ingot at  
5 550 - 600°C for 30 minutes to 24 hours, with higher temperatures requiring shorter hold times. As noted above, optimum homogenisation conditions may depend on the presence and concentration of added Mn.

The homogenised extrusion ingot is hot  
10 extruded, under conditions which may be conventional. The emerging extrusion is quenched, either by water or forced air or more preferably in still air, and subjected to an ageing process in order to develop desired strength and toughness properties.

Ageing typically involves heating the  
15 extrusion to an elevated temperature in the range 150 - 200°C, and holding at that temperature for 1 - 48 hours, with higher temperatures requiring shorter hold times. A surprising feature of this invention is  
20 that the response of the extrusion to this ageing process depends significantly on the rate of heating. A preferred rate of heating is from 10 - 100°C, particularly 10 - 70°C, per hour; if the heating rate is too slow, low throughput results in increased costs;  
25 if the heating rate is too high, the mechanical properties developed are less than optimum. An effect equivalent to slow heating can be achieved by a two-stage heating schedule, with a hold temperature typically in the range of 80 - 140°C, for a time  
30 sufficient to give an overall heating rate within the above range.

When aged to peak strength, extrusions are typically found to have an ultimate tensile strength of at least 240 MPa, often greater than 250 MPa, with  
35 acceptable toughness.

Reference is directed to the accompanying

- 6 -

drawings in which:-

Figure 1 (already referred to) is a compositional plot showing the Aluminum Association specification ranges for Mg and Si for various alloys alongside the alloys of the present invention (the blank rectangle containing the filled circle).

Figure 2 is a bar diagram showing the effect of alloy composition and homogenisation temperature on the maximum extrusion pressure of 250 MPa target alloys extruded into a 5 x 20 mm section.

Figure 3 is a bar diagram showing the effect of alloy composition and homogenisation temperature on the surface roughness measurement of 250 MPa target alloys extruded into a 5 x 20 mm section.

Figure 4 is a bar diagram showing the effect of alloy composition and homogenisation temperature on 20° gloss (reflectivity) measurement of 250 MPa target alloys extruded into 5 x 20 mm section.

Figure 5 is a bar diagram showing the effect of alloy composition on the mechanical properties of 250 MPa target alloys, which had been homogenised for 2 hours at 580°C, extruded into a 5 x 20 mm section, forced air quenched, and aged for 7 hours at 175°C. The properties were measured at the back of the extrusion.

Figure 6 is a graph showing the effect of ramp rate to the ageing temperature (5 hours at 185°C) on the tensile strength of two dilute 6000 series alloys, including a very high excess Si alloy containing no Mn and having a composition within the scope of the present invention.

Figure 7 is a bar diagram showing surface roughness of the alloys extruded in Example 4.

Figure 8 is a bar diagram showing tensile properties of the alloys extruded in Example 4.



- 7 -

EXAMPLE 1

The invention has been tested in the laboratory. Extrusion trials were carried out using an experimental extrusion press, in which the alloys given  
5 in Table 1 below were extruded. These alloys represent a low Mg-containing alloy of the invention, with and without an addition of 0.12% Mn, together with typical AA6063 and AA6106 compositions, again with and without an addition of about 0.12% Mn. The nominal alloy  
10 composition of the invention is shown as a filled circle in the compositional plot of Figure 1.

Extrusion ingots were DC cast and were homogenised for 2 hours at 570°C or 580°C. They were then hot extruded.

15 Extrusion pressure was recorded, and maximum extrusion pressure data for the alloys are given in Figure 2. Thus, this data shows that the extrusion pressure of the alloy type of the invention is significantly lower than that of the AA6106 and AA6063A  
20 alloys. The addition of Mn to the base composition may reduce the extrusion pressure still further, but is found to be dependent upon the precise homogenisation conditions used (see Figure 2).

The surface quality of the extrudate was  
25 assessed using both profilometry and Gloss (reflectivity) measurements, and the data obtained using these techniques are given in Figures 3 and 4. From Figure 3, it can be seen that the lowest value of mean surface roughness (Ra), for a given homogenisation  
30 condition, is produced in extrudate from the optimum alloy composition of the invention (the low Mg, Mn-containing alloy). The same alloy also gives the highest Gloss measurement, again for a given homogenisation treatment. Therefore, the alloy of the  
35 invention has been shown to have the best surface quality of the alloys evaluated.

- 8 -

The tensile properties and Kahn tear toughness of the extrudate from each alloy was evaluated following "peak" ageing (7 hours at 175°C), and the relevant data are shown in Figure 5. It can be  
5 seen from this figure that the tensile properties and the toughness of the alloy of the invention are equivalent to those of the AA6106 and AA6063A alloys.

#### EXAMPLE 2

10 An alloy of composition: 0.65Si-0.33Mg-0.19Fe-0.08Mn was evaluated in extrusion trials. This alloy showed reduced extrudability as compared with "conventional" AA6060 alloys, but the maximum attainable extrusion speed was still relatively high  
15 (up to ~80 m/min) in comparison with AA6063 alloys. The application of two stage ageing practice to extrudate of this alloy showed that the tensile properties could be improved significantly as compared with material aged "conventionally" (see Table 2).

20

#### EXAMPLE 3

The application of a ramped ageing practice to extrusions made of two dilute 6000 series alloys is shown in Figure 6, in which the response of the  
25 extrusions to slow ramp rates is demonstrated. The composition of the alloys were:-

Excess Si AA6060 alloy: 0.35 Mg - 0.52 Si - 0.20 Fe.

Very high excess Si alloy: 0.35 Mg - 0.70 Si  
30 - 0.20 Fe.

#### EXAMPLE 4

The invention has been tested on a commercial scale. Extrusion trials were carried out using 180 mm  
35 diameter billets. The compositions of the trial alloys are given in Table 3.

- 9 -

Surface quality of the extrusions is shown in Figure 7. The experimental alloy of the invention gives a "less rough" surface than either of the other two alloys.

5           Tensile properties of the extrusions, after ageing to peak strength, are set out in Figure 8. The experimental alloy of the invention has properties equivalent to the AA6063A alloy, and their tensile strength well in excess of 250 MPa with acceptable  
10 toughness.

15

20

25

30

35

- 10 -

Alloy	Si	Mg	Fe	Mn	
1	0.74	0.34	0.20	—	High excess Si
2	0.73	0.33	0.20	0.12	
3	0.58	0.49	0.20	—	Excess Si AA6106
4	0.60	0.49	0.19	0.12	
5	0.49	0.63	0.18	—	Balanced AA6063A
6	0.51	0.64	0.19	0.11	

Table 1 - Analysed compositions of the alloys cast in the development programme for an alloy capable of achieving a tensile strength of ~250MPa.

Ageing Practice	0.2% PS (MPa)	UTS (MPa)	elongation (%)	Toughness (kJ/m <sup>2</sup> )
185°C (8 hr cycle)	216	245	10.7	—
3 hrs at 120°C + 5 hrs at 185°C	229	259	10.4	114

Table 2 - Tensile properties and Kahn tear toughness of a high excess Si alloy (0.65Mg-0.33Mg-0.19Fe-0.08Mn, following "conventional" and ramped ageing.

**COMMERCIAL TRIAL: ALLOY COMPOSITIONS**

Alloy	Fe	Si	Fe	Cu	Mn	Cr
AA6063	0.51	0.43	0.17	0.012	0.024	0.001
AA6063A	0.62	0.51	0.16	0.010	0.032	0.001
Experimental Alloy	0.36	0.69	0.19	0.004	0.12	0.001

Table 3

- 12 -

CLAIMS

- 5    1.        An alloy of composition in weight %  
             Mg            0.25 - 0.40  
             Si            0.60 - 0.90  
             Fe            up to 0.35  
             Mn            up to 0.35  
10        Others        up to 0.05 each, 0.15 total  
             Balance Al  
             provided that the Si content is more than  
             0.30% by weight greater than is required to combine  
             with all the Mg and Fe present.
- 15    2.        An alloy of composition in weight %  
             Mg            0.25 - 0.40  
             Si            0.60 - 0.90  
             Mn            0.10 - 0.35  
             Fe            up to 0.35  
20        Others        up to 0.05 each, 0.15 total  
             Balance Al.
3.        An alloy as claimed in claim 1 or claim 2  
          comprising  
             Fe            0.15 - 0.35  
25        Mn            0.10 - 0.25.
4.        An alloy as claimed in claim 1 comprising  
             Mn            0.07 - 0.15.
5.        An extrusion ingot of the alloy of any one of  
          claims 1 to 4, in which Fe is present as  $\alpha$ -AlFeSi.
- 30    6.        An extrusion of the alloy claimed in any one  
          of claims 1 to 4.
7.        An extrusion made from an ingot as claimed in  
          claim 5.
8.        An extrusion as claimed in claim 6 or claim 7  
35    which has after ageing an ultimate tensile strength of  
          at least 240 MPa.

- 13 -

9. An extrusion as claimed in any one of claims 6 to 8 which has been thermally aged, wherein the rate of heating for ageing was 10 - 100°C/hr.

5

10

15

20

25

30

35




Figure 1




Figure 2






Figure 3




Figure 4




Figure 5




Figure 6

# EXPERIMENTAL ALLOY PROPERTIES




Figure 7

Figure 8

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 94/01880

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C22C21/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C22C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 480 402 (SUMITOMO LIGHT METAL IND LTD) 15 April 1992 * Examples 7,13, comparative example 2; page 2, line 54-57 *	1-4
Y	----	5-8
A	US,A,4 808 247 (SKY ALUMINIUM KK) 28 August 1989 * Claim 1; Example 5 of Table 1 *	1-5
Y	BE,A,906 107 (SCHWEIZERISCHE ALUMINIUM AG) 16 April 1987 * Page 1, lines 3-7; claim 1 *	5-8
A	EP,A,0 222 479 (ALCAN INTERNATIONAL LTD) 20 May 1987 * Claim 2 *	1-9
	-----	

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- \* "A" document defining the general state of the art which is not considered to be of particular relevance
- \* "E" earlier document but published on or after the international filing date
- \* "I" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \* "O" document referring to an oral disclosure, use, exhibition or other means
- \* "P" document published prior to the international filing date but later than the priority date claimed

- \* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* "&" document member of the same patent family

Date of the actual completion of the international search

22 November 1994

Date of mailing of the international search report

14. 12 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Pivalica-Bjoerk, P

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/GB 94/01880

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0480402	15-04-92	JP-A- 5247610 JP-A- 4147951	24-09-93 21-05-92
US-A-4808247	28-02-89	JP-B- 6065739 JP-A- 62278256 JP-A- 62278245	24-08-94 03-12-87 03-12-87
BE-A-906107	16-04-87	NONE	
EP-A-0222479	20-05-87	AU-B- 594081 AU-A- 6316986 CA-A- 1292134 JP-B- 4072899 JP-A- 62096639 KR-B- 9404032 US-A- 4861389 US-A- 5223050	01-03-90 02-04-87 19-11-91 19-11-92 06-05-87 11-05-94 29-08-89 29-06-93

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**